

RAGNO  USA

URBAN POSH™ GLAZED PORCELAIN TILE | 3D PRINTING TECHNIQUE | MADE IN THE USA



live inspired

















live inspired

URBAN POSH™

GLAZED PORCELAIN TILE | 3D PRINTING TECHNIQUE | MADE IN THE USA

-  Floor Tile
-  Wall Tile
-  3D Printing Technique
-  Decorative Tile
-  Trim Available
-  Suitable for Outdoors
-  Slight Variation
-  Frost Resistant
-  Abrasion Resistance
-  D.C.O.F. (Wet Areas)
(Minimum 0.42)
-  21% Minimum Recycled Content
-  No VOC



UP46 BI
12"x24"



UP47 BG
12"x24"



UP48 GR
12"x24"




UP49 AN
12"x24"



UP46 BI
Mosaic - Square 2"x2"
12"x12"



UP47 BG
Mosaic - Square 2"x2"
12"x12"



UP48 GR
Mosaic - Square 2"x2"
12"x12"



UP49 AN
Mosaic - Square 2"x2"
12"x12"

Trims



UP46 BI
Bullnose
3"x24"



UP47 BG
Bullnose
3"x24"



UP48 GR
Bullnose
3"x24"



UP49 AN
Bullnose
3"x24"

made in the
USA



Contributes to
LEED Credits

TECHNICAL SPECIFICATIONS

DESCRIPTION	ANSI STANDARD	RESULT	ASTM TEST METHOD
Water Absorption	≤ 0.50%	≤ 0.50%	C373
Frost Resistance	As Reported	Resistant	C1026
Scratch Resistance	MOHS 1-10	8	MOHS SCALE
Breaking Strength	≥ 250 lbf.	≥ 652 lbf.	C648
Facial Dimension	+/- 3.0 % From Nominal	Within Standard	C499
Thickness	≤ 0.04 in (1.02 mm max)	Within Standard	C499
Wedging (Squareness)	+/- 0.50 % or +/- 2.0 mm**	Within Standard	C502
Warping (Flatness)	+/- 0.75 % or +/- 2.3 mm**	Within Standard	C485
Abrasion Resistance	Class 0 - Class V	Class IV	C1027
DCOF - Dynamic Coefficient of Friction (We Areas Only)†	As Reported	Minimum 0.42	DCOF AcuTest SM *
Chemical Resistance	Class A - Class E	Class A	C650
Stain Resistance	Class A - Class E	Class A	C1378

†Dynamic Coefficient of Friction (DCOF) - Water, oil, grease or other fluids create slippery conditions. When installing floors in areas with exposure to these conditions, a minimum D.C.O.F. value of 0.42 is required. Additionally, extra caution is required with regards to product selection and proper maintenance. Visit www.tcnatile.com for complete information regarding the DCOF Acutest test method and values.

*DCOF AcuTest is the industry designation for the test procedure contained in ANSI A137.1 Section 9.6, which has been extensively researched, allows for in-situ field measurements, and is in use at tile manufacturing facilities. It was so named to distinguish it from other DCOF measurements using different instruments and/or protocols.

** Whichever is less

